

C1220 Polyaspartic Resin

Technical Data Sheet

JUNAIMEI NEW MATERIALS | POLYASPARTIC RESIN



聚耐美 | 天冬纯聚脲

Product Description

A solvent-free, low-viscosity, new aliphatic polyaspartic ester resin containing secondary amino groups; comparable to Covestro NH 1220.

Key Features

1. High solids and low viscosity; suitable for high-solids, low-viscosity environmentally responsible coatings, with application solids up to 100%.
2. High reactivity; reacts with HDI trimer to reach tack-free drying in about 5 minutes, improving production efficiency.
3. Coatings show excellent flexibility, flow and leveling, and gloss.
4. Films also provide outstanding weatherability, water resistance, solvent resistance, acid and alkali resistance, and salt-spray resistance.
5. Particularly strong abrasion resistance, with abrasion loss ≤ 20 mg (500 r/1000 g).
6. Excellent adhesion to ABS, PC, PVC and many metals.

Typical Properties

Property	Typical Value	Test Method / Unit
Appearance	Colorless to pale yellow liquid	Visual
Amine value	240-248	
Color value (APHA)	Max. 250	
NH equivalent (g/mol)	230	Theoretical
Equivalent OH content, %	7.4	
Relative density (25 deg C)	1.05	
Viscosity (mPa.s/25 deg C)	60-100	
Solids content	97 +/- 2%	
Flash point	94	deg C

Note: Values shown are typical only and, unless expressly agreed in writing, are not to be regarded as specifications or guaranteed values.

Applications

Waterproofing, anticorrosion coatings, flooring, blade coatings, adhesives, and automotive repair materials.

Packaging

20 kg or 200 kg per drum

Shelf Life

When stored in the original, unopened and undamaged sealed container at temperatures not exceeding 40 deg C, the product has a shelf life of one year.

Handling Notes

1. This product is combustible. Store at low temperature, not above 40 deg C, away from ignition sources and in a cool, dry and well-ventilated area. Protect from moisture, heat and foreign materials. Shelf life is one year.
2. Coatings prepared with this product should be cured for one week before performance testing.

Regulatory Status

Please refer to the Material Safety Data Sheet (MSDS). For chemical inventory information, contact your dedicated sales representative.

Safety Precautions

Please refer to the Material Safety Data Sheet (MSDS), available from your dedicated sales representative.

Health and Safety Information

Appropriate health and safety instructions must be observed when handling chemical products. For products not supplied by the company, follow the industrial hygiene and safety precautions provided by the relevant manufacturer. Before using the products described, read and understand the information on hazards, proper operation and handling. Such information is available from the MSDS, product labels and other sources. For further information, contact your dedicated sales representative or technical information department.

Contact

Junaimei (Shandong) New Materials Co., Ltd.

Junaimei (Shandong) New Materials Co., Ltd.

M 18516800818

T 0534-6836668

E info@junaimei.cn

W www.junaimei.cn

A No. 7, Circular Economy Demonstration Park, Tieying Town, Leling, Dezhou, Shandong, China

Disclaimer

This document and our technical advice, whether given orally, in writing or through testing, are provided in good faith and without warranty. All descriptions, technical information and recommendations contained herein are based on test results we believe to be reliable; however, we do not warrant their accuracy or completeness. Actual test methods and procedures may differ from the listed standard methods. The application, use and processing of our products, and any products made by you based on our technical advice, are beyond our control and therefore remain entirely your responsibility. Our products are sold subject to the general terms and conditions of sale and delivery in effect at the time.